



TEST REPORT TUCHENG

Date: Jun.11,2020	Date of Receipt:	May.22,2020

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages: P1/6 Ref. No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Item: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Protection Efficiency	1	80.20	CNS 14755 Z2125-2011
of Mask(%)	2	80.40	This reflow rate: 85± 4
$(0.075\mu\mathrm{m\ NaCl,CMD})$	3	80.50	This reflow rate: 85± 4 and should refloring to reference only
	4	81.70	be used as reference
	5	80.55	a formal
	6	80.46	
	7	80.70	>
	8	80.50	Q.
	9	81.00	
	10	81.70	
	Ave.	80.77	

Note: Sample description is given by the client: Medical masks

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of

Taiwan Textile Research Institute



Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)





TEST REPORT TUCHENG

Date: Jun.11,2020	Date of Receipt:	May.22,2020
-------------------	------------------	-------------

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages. Pef. No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Item: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Inhalation Resistance	1	75.16	CNS 14755 Z2125-2011
(Pa)	2	76.44	This Flow rate:85± 4
	3	76.44	uner (datefinin)
	4	80.36	CNS 14755 Z2125-2011 This Flow rate:85± 4 Constitution of the used as a formal
	5	77.42	a formal
	6	76.44	
	7	76.44	
	8	76.44	
	9	75.46	
	10	77.42	E a
	Ave.	76.83	
Exhalation Resistance	£ //	74.48	
(Pa)	2	72.52	
	3	71.54	S°.
	4	78.40	
	5	76.44	
	6	72.52	
	7	75.46	
	8	70.56	313
	9	73.50	0
	10	75.46	
	Ave	74.09	

Note: 1mmH2O=9.8Pa.

Note: Sample description is given by the client: Medical masks

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.

Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of

Taiwan Textile Research Institute



Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)





TEST REPORT TUCHENG

Date: Jun.11,2020	Date of Receipt:	May.22,2020

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages: P3/6) Ref. No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Item: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Synthetic Blood Penetration	1	None Seen	CNS 14776 T4038-2003
Pressure: 80 mmHg	2	None Seen	les _f
	3	None Seen	est report is for reference only
	4	None Seen	be used as
	5	None Seen	a formal
	6	None Seen	-
	7	None Seen	-
	8	None Seen	
	9	None Seen	
	10	None Seen	
	11	None Seen	100
	12	None Seen	3
6	13	None Seen	

Note: Sample description is given by the client: Medical masks

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of

Taiwan Textile Research Institute



Certification

Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)





TEST REPORT TUCHENG

Date: Jun.11,2020	Date of Receipt:	May.22,2020

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages. Page No.: No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Itam: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Air Exchange Pressure	1	2.7	CNS 14777 T4039-2003
(mmH2O/cm²)	2	2.6 This	lest .
	3	2.7 docume	ould not is for
	4	2.8	ould not be used as a formal
	5	2.8	a formal
Flammability	Length wise	DNI	CNS 10285 L3196-1995
(as Received)	Width wise	DNI	Method C
	Rating	Grade 1	

Note: "DNI":Did Not Ignite.

Note: Air Exchange Pressure takes 5 masks for testing.

Note: Flammability takes 20 sample for testing.

Note: Sample description is given by the client: Medical masks

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of

Taiwan Textile Research Institute



Director,
Department of Testing and
Certification

Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)





TEST REPORT TUCHENG

Date: Jun.11,2020 Date of Receipt: May.22,2020

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages. Psf. No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Item: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

Test Items		Test Results	Test Methods
Bacterial Filtration	1	99.1	CNS 14775 T4037-2003
Efficiency (BFE)(%)	2	98.5	This test
Staphylococcus aureus	3	98.5	document should not is for
ATCC 6538	4	98.9	be used as reference or
	5	98.6	and should not be used as a format

Note: Control average: 2552 CFU.

Note: Mean particle size: 3.0 μ m.

Note: Testing side: outside of specimen.

Note: Testing area: 39.5 cm².

Note: Flow rate: 28.3 L/min.

Note: Sample description is given by the client: Medical masks

Note: The test report is the test results issued by the testing institution as requested by the consignor, it shall not determine the legitimacy of the product.



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of

Taiwan Textile Research Institute



Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)





TEST REPORT TUCHENG

Date: Jun.11,2020 Date of Receipt: May.22,2020

Report No.: TFF9E452 Quantity: 1PC Page Order/Pages. P6/6) Ref. No.: NIL

Report Title: Jeng Guang Co., Ltd.(T4561)

Item: Mask

Address: No. 26, Jianguo E. Rd., Taoyuan Dist., Taoyuan City 330, Taiwan (R.O.C.)

This less report is for reference only



Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.

- 2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.
- The test report should not be used for public advertisement and commercial promotion.

Authorized by president of Taiwan Textile Research Institute



Department of Testing and Certification, Taiwan Textile Research Institute No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)